

TEST REPORT

NO.: A001R140623064001-6

Date: Jun 27, 2014

Page 1 of 3

Applicant: CHAOREN TECHNOLOGY CO., LTD.

Address: XINLE INDUSTRIAL ESTATE MA'AN TOWN HUIZHOU CITY GUANGDONG PROVINCE CHINA

Report on the submitted sample said to be

Sample name: PACKING ADHESIVE TAPES

Model: /

Item/Lot No.: /

Material: /

Buyer: /

Supplier: /

Manufacturer: /

Sample received date: Jun 23, 2014

Testing period: From Jun 23, 2014 to Jun 27, 2014

Test Requested:

As specified by client, to determine DEHP, DBP, BBP, DINP, DNOP, DIDP and DIBP content in the submitted sample.

Test Method:

Test Item	Test Method	Measuring Instrument
DEHP, DBP, BBP, DINP, DNOP, DIDP and DIBP	US EPA 3540C:1996, US EPA 8270D:2007	GC-MS

Results: Please refer to next page

*****FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S)*****

Signed for and on behalf of
Shenzhen AOV Testing Technology Co., Ltd

Tested by:

Chen Ru Chun, Hugo
Project Leader

Reviewed by:

Luo Jun, Rosary
Vice Technical Supervisor

Approved by:

Liu Lin Wen, Lewis
Technical Supervisor

TEST REPORT


NO.: A001R140623064001-6

Date: Jun 27, 2014

Page 2 of 3

Test Flow:

To Determine DEHP, DBP, BBP, DINP, DNOP, DIDP and DIBP content:



Test Results:

Item	CAS No.	Unit	MDL	Result	
				A	
Di-iso-nonyl phthalate (DINP)	28553-12-0 68515-48-0	mg/kg	50	N.D.	
Di-n-octyl phthalate (DNOP)	117-84-0	mg/kg	30	N.D.	
Bis (2-ethylhexyl) phthalate (DEHP)	117-81-7	mg/kg	30	N.D.	
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	mg/kg	50	N.D.	
Benzyl butyl phthalate (BBP)	85-68-7	mg/kg	30	N.D.	
Dibutyl phthalate (DBP)	84-74-2	mg/kg	30	N.D.	
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg	30	N.D.	

Specimen Description:

A: Transparent adhesive tape

Note:

- mg/kg = ppm
- N.D.=not detected(<MDL)
- MDL=Method Detection Limit
- Photo is included.


TEST REPORT

NO.: A001R140623064001-6

Date: Jun 27, 2014

Page 3 of 3

Photograph of Sample



End of Report

SHENZHEN AOV TESTING TECHNOLOGY CO.,LTD

1F East,2-6F, Block 5, Yuanrou Lane, Tanglang, Taoyuan Street, Nanshan District, Shenzhen, Guangdong, China
Tel: +86-755-8600 8000 Fax: +86-755-8600 8282 Http://www.aovt.com Postcode: 518055

(Attention is drawn to the terms and conditions printed overleaf)

Hotline
400 700 8600